



OAK RIDGE NATIONAL LABORATORY

operated by

UNION CARBIDE CORPORATION

for the

U.S. ATOMIC ENERGY COMMISSION



OAK RIDGE NATIONAL LABORATORY LIBRARIES



3 4456 0549250 7

ORNL - TM - 1146

COPY NO. - /

DATE - June 11, 1965

PRODUCTION OF A LOW-BORON HEAT OF HASTELLOY N

W. R. Martin, H. E. McCoy, and J. R. Weir

CENTRAL RESEARCH LIBRARY
DOCUMENT COLLECTION

LIBRARY LOAN COPY

DO NOT TRANSFER TO ANOTHER PERSON

If you wish someone else to see this
document, send in name with document
and the library will arrange a loan.

NOTICE This document contains information of a preliminary nature
and was prepared primarily for internal use at the Oak Ridge National
Laboratory. It is subject to revision or correction and therefore does
not represent a final report.

LEGAL NOTICE

This report was prepared as an account of Government sponsored work. Neither the United States, nor the Commission, nor any person acting on behalf of the Commission:

- A. Makes any warranty or representation, expressed or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights; or
- B. Assumes any liabilities with respect to the use of, or for damages resulting from the use of any information, apparatus, method, or process disclosed in this report.

As used in the above, "person acting on behalf of the Commission" includes any employee or contractor of the Commission, or employee of such contractor, to the extent that such employee or contractor of the Commission, or employee of such contractor prepares, disseminates, or provides access to, any information pursuant to his employment or contract with the Commission, or his employment with such contractor.

ORNL-TM-1146

Contract No. W-7405-eng-26

METALS AND CERAMICS DIVISION

PRODUCTION OF A LOW-BORON HEAT OF HASTELLOY N

W. R. Martin, H. E. McCoy, and J. R. Weir

OAK RIDGE NATIONAL LABORATORY
Oak Ridge, Tennessee
operated by
UNION CARBIDE CORPORATION
for the
U.S. ATOMIC ENERGY COMMISSION

OAK RIDGE NATIONAL LABORATORY LIBRARIES



3 4456 0549250 7

PRODUCTION OF A LOW-BORON HEAT OF HASTELLOY N

W. R. Martin, H. E. McCoy, and J. R. Weir

Current mechanisms for the irradiation embrittlement of structural alloys at elevated temperature are generally associated with the production of helium by (n,α) reactions. In most reactor environments the helium is generated from the transmutation of ^{10}B . Boron is generally present in nickel-base alloys at concentrations in the range of 5 to 80 ppm by weight. These concentrations are above those that have been observed to produce deleterious quantities of helium in stainless steels.

The Stellite Division of Union Carbide has melted a 75-lb heat of Hastelloy N, using a practice designed to produce low residuals of boron, oxygen, nitrogen, hydrogen, silicon, and sulfur. This vacuum-induction heat, designated heat 65-552, was melted using an alumina crucible. Since no deliberate additions of boron were made in the melting practice, analysis of the final heat and the raw materials should lead to discovery of the source of boron in the alloy. These data are given in Table 1. The concentration of boron is much less than the normal 5 to 80 ppm. It is apparent that most of the boron was not introduced into the alloy from the raw materials listed in Table 1. Approximately 84% of the boron in the ingot was introduced by some other means. There are perhaps several other sources but a prime suspect is the alumina crucible. Future work should help define further the probable sources of boron.

It has been demonstrated that a heat of Hastelloy N can be produced in 50 to 75-lb ingot sizes that contain substantially lower quantities of boron than is normally found in these grades of material. It therefore seems probable that larger ingots in the range of 10,000 lb can also be produced which could offer improved properties for reactor application at elevated temperatures.

Table 1. Boron Analyses

Material	Boron Concentration (ppm by weight)	Approximate Boron Contribution to Alloy (ppm by weight)
Hastelloy N	0.90	
Total Raw Materials in Alloy	0.14	0.144
Electrolytic nickel	0.08	0.057
Molybdenum rondels	0.25	0.042
Electrolytic chromium	0.06	0.005
Armco Iron	0.45	0.019
Electrolytic manganese	0.30	0.002
Aluminum shot	3.50	0.016
Nickel-magnesium	0.08	0.0002
Graphite	4.50	0.003

INTERNAL DISTRIBUTION

- | | | | |
|-------|-------------------------------|--------|------------------|
| 1-3. | Central Research Library | 24. | J. H Frye, Jr. |
| 4-5. | ORNL - Y-12 Technical Library | 25. | G. Hallerman |
| | Document Reference Section | 26-28. | M. R. Hill |
| 6-15. | Laboratory Records | 29. | H. G. MacPherson |
| 16. | Laboratory Records, R.C. | 30. | W. R. Martin |
| 17. | ORNL Patent Office | 31. | H. E. McCoy |
| 18. | G. E. Boyd | 32. | R. E. McDonald |
| 19. | R. B. Briggs | 33. | P. Patriarca |
| 20. | F. L. Culler | 34. | A. Taboada |
| 21. | J. E. Cunningham | 35. | A. M. Weinberg |
| 22. | W. W. Davis | 36-55. | J. R. Weir |
| 23. | D. A. Douglas | | |

EXTERNAL DISTRIBUTION

- 56-57. D. F. Cope, AEC, Oak Ridge Operations Office
- 58-60. J. M. Simmons, AEC, Washington
- 61. Division of Research and Development, AEC, ORO
- 62-76. Division of Technical Information Extension