



Alloy Development for Irradiation Performance

Semiannual Progress Report
For Period Ending March 31, 1983

U.S. Department of Energy
Office of Fusion Energy

CONTENTS

FOREWORD	iii
1. ANALYSIS AND EVALUATION STUDIES	1
1.1 Materials Handbook for Fusion Energy Systems (McDonnell Douglas Astronautics Company and Westinghouse Hanford Company)	2
<i>During the past year the handbook effort has been directed towards developing data sheets. For this year the effort has been to incorporate those data sheets into the handbook. Substantial progress has been made towards the achievement of this goal with the publication of more than 31 new data pages covering the properties of bulk graphites, liquid lithium, and ceramic lithium compounds.</i>	
1.2 Low Activation Approaches to Materials Development (Westinghouse Hanford Company)	3
<i>An effort has been initiated to develop low-activation alloys for fusion reactor service. Several major compositional regimes have been identified for development. The approach employed has been to develop low activation alloys via routes which may mitigate previously identified material problems.</i>	
1.3 An Assessment of Martensitic Stainless Steels for Low Activation Status (GA Technologies)	5
<i>A design equation gives allowable amounts of impurities in martensitic steels with 12% Cr, to permit trade-off of strengthening agents when some additions produce unacceptable levels of impurities.</i>	
2. TEST MATRICES AND METHODS DEVELOPMENT	11
2.1 Neutron Source Characterization for Materials Experiments (Argonne National Laboratory)	12
<i>Neutron fluxes and energy spectra agree quite well for HFIR irradiations CTR-31, -32, -34, and -35. Reaction rates in CTR-32 were corrected by improved burnup calculations. Helium production is being revised slightly because of new ⁵⁹Ni cross sections. Dosimetry for several irradiation experiments is summarized.</i>	
2.2 Neutronics Calculations in Support of ORR-MFE-4 Spectral Tailoring Experiments (Oak Ridge National Laboratory)	19
<i>New scaling factors have been obtained to force agreement between the experimentally measured and calculated fluences. As of March 31, 1983, these factors yield 89.6 at. ppm He (not including 2.0 at. ppm He from ¹⁰B) and 6.18 dpa for type 316 stainless steel in ORR-MFE-4A and 57.7 at. ppm He and 4.48 dpa in ORR-MFE-4B.</i>	
2.3 Operation of the ORR Spectral Tailoring Experiments ORR-MFE-4A and ORR-MFE-4B (Oak Ridge National Laboratory)	21
<i>The specimens contained in the ORR-MFE-4A experiment have been in reactor for an equivalent of 529.3 d at 30 MW reactor power, with temperatures of 400 and 330°C. The ORR-MFE-4B experiment, with specimen temperatures of 500 and 600°C, has operated for an equivalent of 424 d at 30 MW reactor power. It was removed from the reactor October 21, 1982, for specimen inspection and transfer to a new capsule.</i>	
2.4 Irradiation of Miniature Charpy Specimen of 12 Cr-1 MoW: Experiment HFIR-CTR-46 (Oak Ridge National Laboratory)	23
<i>The HFIR-CTR-46 experiment contains miniature Charpy V-notch specimens of the national fusion heat of 12 Cr-1 MoW steel. Irradiation at 300°C and 400°C will achieve a midplane damage level of 10 dpa.</i>	
2.5 High Fluence Irradiation of Ferritic Steel Charpy Specimens: Experiments HFIR-CTR-47 and -48 (Oak Ridge National Laboratory)	25
<i>The HFIR-CTR-47 and -48 experiments are companions of the earlier experiments HFIR-CTR-34 and -35 to achieve displacement damage levels up to 40 dpa in 9 Cr-1 MoVNb and 12 Cr-1 MoW steels. Irradiation temperatures are 300 and 400°C. Nickel-doped alloys are included to assess the influence of helium on post-irradiation impact behavior.</i>	

3.	PATH A ALLOY DEVELOPMENT -- AUSTENITIC STAINLESS STEELS	27
3.1	Swelling and Microstructural Development of Path A PCA and Type 316 Stainless Steel Irradiated in HFIR (Oak Ridge National Laboratory)	28
	<i>Evaluation of swelling of PCA variants and 20%-cold-worked (N-lot) type 316 stainless steel (CW 316) irradiated at 300-600°C was extended to -22 dpa. Voids continued to develop with increased fluence in PCA-A1, -B1, and CW 316. Void swelling saturated in PCA-BZ at -10 dpa at 600°C and did not develop in PCA-A3 up to 22 dpa. A stable structure of fine titanium-rich MC developed during irradiation of PCA-A3, while preexisting MC precipitate in PCA-B2 redistributes during irradiation.</i>	
3.2	Grain Boundary Microstructural Development and Stability for Various Pretreatments of Path A Prime Candidate Alloy Irradiated in HFIR (Oak Ridge National Laboratory)	39
	<i>Irradiation to 22 dpa in HFIR at 500 and 600°C produced resolvable grain boundary bubbles in Path A PCA and CW 316. PCA-A1 had the coarsest bubble structure at 600°C and no MC precipitate. Medium to coarse distributions of MC developed at the boundaries by heat treatment of PCA-B1 and -B2 were stable under irradiation; very fine bubbles clustered about these particles at 600°C. The PCA also resisted sigma formation, compared with CW 316 (DO heat;) or SA 316 and 316 + Ti (R1 heat) irradiated in HFIR.</i>	
3.3	The Tensile Properties of Unirradiated Path A Prime Candidate Alloy (Oak Ridge National Laboratory)	49
	<i>The tensile properties of Path A PCA in the A1, A3, and B2 conditions have been determined at temperatures from room temperature to 700°C. The 25%-cold-worked alloy, PCA-A3, showed strength values similar to those of the reference heat of 20%-cold-worked 316 stainless steel but exhibited a lower ductility in the 200-300°C range.</i>	
3.4	Effect of the Microstructure on Tensile Properties of Type 31K Stainless Steel (Oak Ridge National Laboratory)	53
	<i>A series of tensile specimens that had been given different thermal and mechanical processing treatments was irradiated in the ORR at 250, 290, 450, and 500°C to a neutron fluence of about 6.8×10^{25} neutrons/m² (>0.1 MeV); (-5 dpa and 40 at. ppm He). The tensile properties of irradiated and unirradiated steel with 20, 30, and 50% cold work were determined at the irradiation temperatures.</i>	
3.5	Tensile Properties and Swelling of 20%-Cold-Worked Type 31h Stainless Steel Irradiated in HFIR (Oak Ridge National Laboratory)	60
	<i>Immersion density and elevated-temperature tensile properties were determined on 20%-cold-worked type 316 stainless steel irradiated in the HFIR to fluences of 1.8 to 3.7×10^{26} neutrons/m² (>0.1 MeV), which resulted in 16 to 32 dpa and 1250 to 2000 at. ppm He. These data were combined with the data obtained in two previous experiments, one to similar fluences and one to higher fluences (up to 6.3×10^{26} neutrons/m²).</i>	
3.6	Fracture Strain of 20%-Cold-Worked Type 316 Stainless Steel Under Irradiation in EBR-II (Oak Ridge National Laboratory)	65
	<i>Swelling-driven fracture strain specimens of 20%-cold-worked 316 stainless steel were irradiated to a fluence of 5×10^{26} neutrons/m² (>0.1 MeV) in EBR-II at 430, 550, and 625°C. Fracture strain was not a function of fluence or strain rate but only of temperature. Fracture strain was found to be 6% at 550°C and 1% at 625°C. All fractures were intergranular, but a notched specimen irradiated at 550°C showed some evidence of ductility.</i>	
4.	PATH B ALLOY DEVELOPMENT -- HIGHER STRENGTH Fe-Ni-Cr ALLOYS	
	<i>No contributions.</i>	

5.	PATH C ALLOY DEVELOPMENT— REACTIVE AND REFRACTORY ALLOYS	73
5.1	Mechanical Property Evaluations of Path C Vanadium Scoping Alloys (Westinghouse Electric Corporation)	74
	<i>This report updates the data on the creep/stress rupture of the vanadium-base scoping alloys containing zero, 600 wppm and 1200 wppm additional oxygen. The conclusions drawn earlier that V-15Cr-5Ti shows superior creep/stress rupture properties to V-20Ti and VARSTAR-7 alloys and that addition of 1200 wppm oxygen has no major effect on the creep rupture properties remain valid. The additional fmctography presented here confirms the ductile nature of these alloys.</i>	
5.2	Weldability of Path C Vanadium Alloys (Westinghouse Electric Corporation)	81
	<i>Gas tungsten arc welds were prepared for each of the three vanadium-base [Path C] scoping alloys using semi-automatic, full penetration, bead-on-sheet welds. The bend ductile-brittle transition temperatures (DBTTs) of these welds and base metal specimens were determined. In terms of weldability the alloys were maked: (best) V-20Ti, V-15Cr-5Ti, VANSTAR-7. The bend DBTT values for weld specimens were: V-20Ti, -196/+150°C; V-15Cr-5Ti, -20/+50°C; VANSTAR-?, -75/-50°C, for longitudinal/transverse bend tests.</i>	
5.3	Evaluations and Development of Vanadium-Base Alloys for Fusion Reactor Applicatinns (Argonne National Laboratory)	87
	<i>The corrosion of "pure" V and V-5Ti, V-15Cr and V-15Cr-5Ti alloys at 725 K and 825 K in flowing helium containing 10 ppm water was determined for exposure times that yielded a steady-state corrosion mte. The experimentally determined corrosion mtes for the V and V-base alloys were compared with the corrosion rate obtained for PCA stainless steel under the same environmental conditions. These results showed that the steady-state corrosion mtes for the V-15Cr alloy and V-15Cr-5Ti alloy were low but approximately one order of magnitude greater than the steady-state corrosion mte determined for the PCA stainless steel. Also, the temperature dependence of the electrical resistivity for V and V-15Cr-5Ti alloy was determined for temperatures ranging from 77 K to 1000 K.</i>	
6.	INNOVATIVE MATERIAL CONCEPTS	91
6.1	Status of Scaleanup of an Iron-Base Long-Range-Ordered Alloy (Oak Ridge National Laboratory)	
	<i>Semiproduction scaleanup of the iron-base alloy LRO-37 has been successfully completed. Three ingots of the alloy were produced by a commercial source, hot forged to slab, then milled to 3.3-, 1.6-, and 0.8-mm sheet stock. The hiah-purity material contained MC-type carbides, and M₂(C,N)-type carbides were observed in commercial-grade alloy.</i>	
6.2	Bend Ductility of Iron-Base Long-Range-Ordered Alloys After Irradiation in HFIR (Oak Ridge National Laboratory)	94
	<i>Three iron-base LRO alloys with base composition (Fe,Ni)₃V tested at 600°C exhibited intergranular fracture and reduced bend ductilities after irradiation to 10 dpa at 600°C in HFIR. The embrittlement extended to lower temperatures as the damage level increased. The weakness of the grain boundaries may be mused by the presence of helium, segregating elements, VC particles, or a combination of these factors.</i>	
7.	PATH E ALLOY DEVELOPMENT — FERRITIC STEELS	99
7.1	Preliminary Transmission Electron Microscopy of 12 Cr-1 MoVW Irradiated to 40 dpa in HFIR (Oak Ridge National Laboratory)	100
	<i>Specimens of 12 Cr-1 MoVW steel were irradiated in HFIR to 40 dpa at 400 and 600°C. Preliminary microstructural examination indicates significant cavity formation in this steel, and this is attributed in part to the helium produced during irradiation.</i>	

- 1.2 Elevated-Temperature Tensile Properties of 12 Cr-1 MoW Steel Irradiated in the ERR-11, AD-2 Experiment (Oak Ridge National Laboratory) 104
- The effect of irradiation on the tensile properties of 12 Cr-1 MoW steel in two normalized-and-tempered conditions was determined for specimens irradiated in EBR-II at 330 to 550°C. Tests were conducted at room temperature and at the irradiation temperature. Irradiation to approximately 11 dpa increased the ultimate tensile strength for each irradiation temperature; an increased yield stress was noted only at the lowest temperature.*
- 7.3 Fatigue Crack Growth in Path E Alloys (Westinghouse Hanford Company) 108
- Fatigue crack growth tests on unirradiated HT-9, HT-9 weldments and 9Cr-1Mo have been conducted in helium at temperatures up to 550°C and at cyclic frequencies of 6.67 and 0.667 s⁻¹. Little differences in crack growth behavior between the three materials were observed at any single condition. However, higher crack growth rates were evident at the lower stress intensity factors at 0.667 s⁻¹ on specimens tested at 300°C compared to 550°C. No effect of irradiation was observed on HT-9 irradiated to 13 dpa at 550°C and tested at 550°C at 6.67 s⁻¹.*
- 7.4 Fracture Toughness of Irradiated HT-9 Weld Metal (Westinghouse Hanford Company) 125
- Fracture toughness tests using electrochemical techniques on HT-9 weld material irradiated to a fluence of 2.1×10^{22} n/cm² (E > 0.1 MeV) at 390°C were performed at 93, 205, 316 and 427°C. Testing of HT-9 welds irradiated at 450, 500 and 550°C was performed at 205°C. The test results show that irradiation for the 390°C irradiation condition, testing at 93 and 427°C showed little change in fracture toughness after irradiation. However, testing at 200 to 300°C resulted in higher toughness, higher than that of unirradiated material.*
- 7.5 Effect of Specimen Size and Material Condition on Charpy Impact Properties of 9 Cr-1 MoVNb (Oak Ridge National Laboratory) 131
- Charpy-impact properties were determined on full- and subsize specimens of normalized-and-tempered as well as quenched-only 9 Cr-1 MoVNb steel. The subsize specimen produced consistently smaller fractional drops in the upper-shelf energy and larger shifts in the transition temperature than did the full-size specimen. Area and volumetric normalizations of the specimen size effect were also performed.*
- 7.6 The Toughness of Simulated Heat-Affected Zone Microstructures in HT-9 (ESK Melt Practice) (Sandia National Laboratories, Livermore) 13R
- The toughness behavior of the heat-affected zone in the ESR National Fusion Heat was determined using Gleeble-simulated microstructures. Two regions of the HAZ were evaluated; one region represents the portion of the HAZ nearest the fusion zone, the other corresponds to a region which is heated only slightly above the upper critical temperature. Charpy V-notch results indicated that following a PWHT at 760°C for 1 hour both regions of the HAZ exhibit superior toughness behavior to that of the quench-and-tempered base material. The upper shelf toughness increased 20-40 Joules and the DBTT decreased nearly 20°C relative to the base metal. The toughness of both the ESR base material and HAZ microstructures was superior to that of the AOD-processed National Fusion Heat, which had been previously tested in a similar manner.*
- 7.7 Fractographic Examination of Cracking in HT-9 Multipass Welds (Sandia National Laboratories, Livermore) 146
- To be reported in the next semiannual report.*
- 7.8 The Influence of Prior Cold Work on the Hydrogen Charged Tensile Fracture of a 12Cr-1Mo Steel (Sandia National Laboratories, Livermore) 147
- Swaging and retempering improved the tensile ductility of quench-and-tempered 12 Cr-1 Mo steel and eliminated intergranular cracking, whether or not the material was hydrogen charged.*

7.9	The Effect of Preheat on the Microstructure, Hardness and Toughness of HT-9 Weldments (GA Technologies)	155
	<i>Preheating at 100°C before welding HT-9 increased toughness by 13.5 J and lowered the ductile-to-brittle transition temperature by 14°C (to -12°C) compared with pre-heating at 400°C. Scanning electron microscopy showed that slower cooling in the weld after the 400°C preheat increased dendrite spacing significantly by depleting the surrounding matrix of Cr, Mo, and W and increasing the Ni.</i>	
7.10	An Assessment of Fabrication Methods for an HT-9 First Wall/Blanket Module (GA Technologies)	163
	<i>A study of the TASKA tandem mirror reactor design shows that HT-9 has adequate fabricability to meet the design requirements as a structural material for the first wall and blanket.</i>	
7.11	Irradiation of ESR Alloy HT-9 and Alloy 9Cr-1Mo(Mod.) Plates for Fracture Toughness Assessment (Naval Research Laboratory)	172
	<i>During this period, irradiation exposures at 300°C and 150°C to $8 \times 10^{19} n/cm^2$, $E > 0.1 MeV$, were undertaken for the Alloy HT-9 and Alloy 9Cr-1Mo(Mod.) plates, respectively. Specimen types include tension, Charpy-V(C_V), fatigue precracked Charpy-V(PCC_V) and half-size Charpy-V specimens and, in the case of the Alloy 9Cr-1Mo(Mod.), 2.54 mm thick compact tension specimens.</i>	
8.	STATUS OF IRRADIATION EXPERIMENTS AND MATERIALS INVENTORY	175
8.1	Irradiation Experiment Status and Schedule (Oak Ridge National Laboratory)	176
8.2	Fusion Program Research Materials Inventory (Oak Ridge National Laboratory, McDonnell Douglas Company, and GA Technologies)	
9.	MATERIALS COMPATIBILITY AND HYDROGEN PERMEATION STUDIES	185
9.1	Corrosion of Path A PCA, Type 316 Stainless Steel, and 12 Cr-1 MoW Steel in Flowing Lithium (Oak Ridge National laboratory)	186
	<i>In lithium thermal convection loop (TCL) experiments, weight losses and dissolution rates of annealed and cold-worked path A prime candidate alloy IPCAJ were slightly higher than those of type 316 stainless steel. The depth of the ferrite layer on type 316 stainless steel was constant between 3700 and 9000 h at 600°C but not at 570°C. Nitrogen level between 9 and 130 wt ppm in lithium did not affect short-term weight losses of type 316 stainless steel. The 12 Cr-1 MoW steel showed measurable but small weight losses in thermally convective lithium between 350 and 500°C.</i>	
9.2	Corrosion of Type 316 Stainless Steel in Static Pb-17 at. % Li (Oak Ridge National Laboratory)	191
	<i>The surface morphology and composition of type 316 stainless steel specimens exposed to static Pb-17 at. % Li between 400 and 700°C were studied. Preliminary results indicated nickel depletion throughout this temperature range and relative chromium surface enrichment for those specimens suffering the highest weight losses.</i>	
9.3	Environmental Effects on Properties of Structural Alloys (Argonne National laboratory)	195
	<i>Corrosion data are presented for several austenitic and ferritic steels exposed at temperatures between 700 and 755 K in flowing lithium and Pb-17 Li environments. The results indicate that (dissolution rates for both steels are an order of magnitude greater in Pb-Li than in lithium. Tensile data for cold-worked Type 316 stainless steel show that a flowing environment has no effect on the tensile properties of Type 316 steel at temperatures between 473 and 773 K.</i>	

9.4	Compatibility of Vanadium Alloys with High-Temperature Water (Oak Ridge National Laboratory)	201
	<i>Weight gains of Path C vanadium alloys (V-20% Ti, V-15% Cr-5% Ti, VANSTAR-71 exposed to 300°C inter for 100 h were relatively small and not significantly affected by hydrogen overpressure.</i>	
9.5	Compatibility Studies of Structural Alloys with Solid Breeder Materials (Argonne National Laboratory)	204
	<i>Compatibility tests between ferritic HT-9 alloy or Fe-9Cr-1Mo steel and Li₂O pellets in a flowing helium environment indicate that the reaction rates in helium containing 93 ppm H₂O are greater than in helium with 1 ppm H₂O. All alloy specimens gain weight whereas the Li₂O pellets lose weight after exposure. Data on the reaction kinetics and metallographic evaluation of the alloy specimens are presented.</i>	