



Damage Analysis and Fundamental Studies

Quarterly Progress Report
January-March 1984

May 1984

**U.S. Department of Energy
Office of Energy Research
Office of Fusion Energy
Washington, DC 20545**

CONTENTS

	<u>Page</u>
Foreword	iii
CHAPTER 1: IRRADIATION TEST FACILITIES	1
1. <u>RTNS-II Irradiations and Operations (LLNL)</u>	2
<i>Irradiations were performed for 13 different experimenters during this quarter. An investigation is underway into the implosion of two 50-cm targets. An isotransformer and a target water system malfunctioned but are back in service. The HEDL furnace shut down due to vacuum leak. The fourth U.S.-Japan Steering Committee meeting was held February 27-28 at RTNS-II.</i>	
CHAPTER 2: DOSIMETRY AND DAMAGE PARAMETERS	4
1. <u>Hafnium Core Piece Test in ORR-MFE4 (ANL)</u>	5
<i>Test results show a thermal shielding of 40%, an epithermal effect of 56%, and a fast neutron reduction of about 7%. Flux gradients are reported with and without the hafnium liner.</i>	
2. <u>Measurement of $^{54}\text{Fe}(n,2n)^{53}\text{Fe}$ Cross Section Near Threshold (ANL)</u>	11
<i>The threshold for this reaction, a producer of long-lived radioactivity from ^{53}Mn, falls quite close to the centroid of the neutron energy distribution emitted by a D-T plasma. This makes the reaction rate quite sensitive to the ion temperature of the plasma; hence these measurements will be used in a new method for measuring D-T plasma ion temperatures.</i>	
3. <u>Helium Generation Measurements for EBR-II and ORK (RI-ESG)</u>	14
<i>Helium generation measurements for Fe, Cu, and Ti samples show significant differences from helium concentrations calculated using ENDF/B-V cross-section evaluations.</i>	

	<u>Page</u>
CHAPTER 3: REDUCED ACTIVATION MATERIALS	17
1. <u>Swelling Behavior of Manganese-Bearing Steel AISI 216 (HEDL)</u>	18
<p><i>The inclusion of 8.5 wt% manganese in AISI 216 (Fe-6.7Ni-8.5Mn-20Cr-2.7Mo-0.32Si) does not appear to alter the swelling behavior from that found to be typical of austenitic alloys with comparable levels of austenitite-stabilizing elements.</i></p>	
CHAPTER 4: FUNDAMENTAL MECHANICAL BEHAVIOK	23
1. <u>Correlation of AISI 316 Stainless Steel Yield Strength with Irradiation-Induced Microstructure (HEDL)</u>	24
<p><i>Improvements in the correlation of change in yield strength in AISI 316 stainless steel with microstructure were effected by re-examining the role of short-range obstacles. It is concluded that large changes in yield strength may be produced in high swelling materials.</i></p>	
2. <u>A Kate-Theory Model for the Evolution of Network Dislocations in Irradiated Metals (U. of Wisconsin)</u>	38
<p><i>The growth of dislocation loops and the climb of edge dislocations can result both in an increase of dislocation line length as well as in the annihilation of dislocation dipoles. These two competing processes form the basis of an evolution model for the dislocation network, which was fitted to experimental data for the dislocation density in irradiated type 316 stainless steels. Predictions are made for the dislocation evolution in ferritic steels.</i></p>	
3. <u>Relations Among Tensile Test Temperature and Strain Kate in the Fracture of Helium-Irradiated Type 316 Stainless Steel (U. of Virginia)</u>	51
<p><i>Conducting one tensile test at two temperatures has shown that a given crack propagates intergranularly at 700°C and immediately changes to transgranular propagation when the temperature is lowered to 550°C, It is shown that this temperature effect is strain rate sensitive and that helium embrittlement is a dynamic phenomenon likely dependent on submicroscopic helium clusters rather than helium bubbles.</i></p>	

	<u>Page</u>
4. <u>Effective Thermophysical and Elastic Properties of Materials with Voids (HEDL)</u>	58
<i>Appropriate equations are given to describe the influence of voidage on thermal and electrical conductivity and on shear, bulk and Young's moduli and Poisson's ratio.</i>	
CHAPTER 5: COKKELATION METHODOLOGY	70
1. <u>Constitutive Design Equations for Thermal Creep Deformation of HT-9 (UCLA)</u>	71
<i>Design equations are given for HT-9 for rupture time and rupture strain as a function of stress and temperature, and creep strain as a function of time, stress, and temperature.</i>	
2. <u>OWR/RTNS-II Low-Exposure Spectral Effects Experiment (HEDL)</u>	76
<i>Irradiation of miniature flat tensile specimens has begun at RTNS-II on Fe, Cu, 316 SS and A302B pressure vessel steel. Comparison irradiations will be performed at OWR at the same temperatures, 90 and 290°C.</i>	
3. <u>Image Interaction Between a Prismatic Dislocation Loop and a Bubble (U. of Wisconsin)</u>	80
<i>The elastic interaction between a spherical cavity and a prismatic dislocation loop has been derived. In spite of the complexity of the elasticity solution, the image interaction can be written in a relatively simple form and be evaluated readily.</i>	
4. <u>Stability of Helium-Vacancy Clusters During Irradiation (UCLA)</u>	87
<i>The stability of helium-vacancy clusters, determined by a continuum approach, was used to define regimes of temperature and He/dpa for spontaneous and delayed nucleation. Applications are made to HFIR, EBH-11, and ion irradiations.</i>	
5. <u>Fundamental Alloy Studies (HEUL)</u>	93
<i>A series of four alloy groups has been produced to investigate the origin of swelling and creep resistance in the Invar regime of the Fe-Ni-Cr austenitic system and to explore the possible existence of high swelling resistance in the corresponding Fe-Cr-Mn austenitic system.</i>	

	<u>Page</u>
6. <u>Swelling Behavior of Titanium-Modified AISI 316 Alloys (HEDL)</u>	102
<p><i>It appears that titanium additions to stainless steels covering a wide compositional range around the specifications of AISI 316 result only in an increased delay period before neutron-induced void swelling proceeds. Once swelling is initiated, the post-transient behavior of both annealed and cold-worked steels is quite consistent with that of AISI 316.</i></p>	
CHAPTER 6: FUNDAMENTAL STUDIES OF SPECIAL PURPOSE MATERIALS	109
1. <u>Mechanical Properties and Microstructures of High-Strength Copper Alloys Following Thermal Annealing (U. of Wisconsin)</u>	110
<p><i>Vickers microhardness measurements on as-received AMZIRC and AMAX-MZC copper alloys as a function of annealing time and temperature indicate that both alloys have an unirradiated recrystallization temperature of about 475°C.</i></p>	
2. <u>Comparison of Thermal and Irradiated Behavior of High-Strength, High-Conductivity Copper Alloys (U. of Wisconsin)</u>	117
<p><i>Ion irradiation results imply that MZC and AMZIRC copper alloys may undergo a serious degradation in mechanical properties when exposed to irradiation at temperatures around 400°C.</i></p>	
3. <u>Irradiation of Copper Alloys in FFTF (HEDL)</u>	133
<p><i>Miniature tensile specimens and TEM disks of nine copper-base alloys in thirteen material conditions are being irradiated in FFTF at 450°C.</i></p>	
4. <u>Comparison of Neutron- and Gamma-Irradiation Damage in Organic Insulators (LANL)</u>	135
<p><i>Flexural mechanical properties were measured at 75 K of one polyimide and two epoxy-based materials irradiated at 4 K at IPNS-II. Some differences were found when compared with the effects of gamma irradiation.</i></p>	