DOE/ER-0046/5

JLS 11-17

Damage Analysis and Fundamental Studies

Quarterly Progress Report
Jan-Mar 1981

May 1981

U.S. Department of Energy
Assistant Secretary for Energy Technology
Office of Fusion Energy
Washington, DC 20545

CONTENTS

Page

Forward

Figures

Tables

CHAPTER 1. IRRADIATION TEST FACILITIES

1. Rotating Target Neutron Source (RTNS)-II Operations (LLNL) 3

Irradiations were performed for eight different experimenters from five different laboratories. These include five "piggy-back" experiments. No major unscheduled outages occurred during this period.

2. Fusion Materials Irradiation Test (FMIT) Facility (HEDL) 5

Evaluation of deuteron-induced activation of gold and aluminum was done and residual doses were calculated.

CHAPTER 2. DOSIMETRY AND DAMAGE PARAMETERS

1. Dosimetry Results for the ORR-MFE2 Experiment (ANL) 13

Dosimetry results are presented for the ORR-MFE2 irradiation. There appears to be no spectral shift from our more complete spectral measurement at low power in January 1979. The maximum fluence (Level 4) was 1.75 x 10^{22} n/cm^2.

2. Helium Generation Cross Sections for Fast Neutrons (RIES) 19

Total helium generation cross sections have been determined for Mo, Zr, V, and the seven separated isotopes of Mo in the 14.8-MeV RTNS-I neutron spectrum, and all helim analyses have been completed for the helium accumulation dosimetry materials irradiated in the RTNS-II neutron characterization experiment.

CONTENTS (Cont'd)

Page

3. International Comparison of Dosimetry Cross Sections (REAL-80) (ANL) 24

The progress of the international REAL-80 Project to compare dosimetry data and techniques is discussed. Detailed cross section comparisons with W. L. Zijp (ECN, Petten) have revealed some minor errors in our multigroup processing code, which have now been corrected.

4. Displacement Damage Calculations (ANL) 29

Displacement cross sections are now being revised for 25 elements of interest to the fusion materials program. All cross sections are derived from ENDF/B-V. A new model for (n,γ) capture has been developed and beta-decay effects are also being included.

5. Specified-Projectile Displacement Function Results for MgO, Al_2O_3 and TaO (LANL) 38

Analysis of displacement cascades in MgO, Al_2O_3 and TaO is reported using data obtained with the specified-projectile displacement function. This function describes the specific collision events that produce displacements. The results show that the importance of specific collision-pairs in producing displacements is a function of initial PKA energy and mass ratio.

6. Damage Parameter Calculations (HEDL) 44

An examination was made of potential self-shielding corrections to calculated displacement rates for specimens irradiated in FFTF. Monte Carlo calculations show that for 5-cm Fe spheres the volume averaged displacement rates will be about 15% lower than inferred from a knowledge of the surface flux and data from small samples.

7. A Comparison of Simulated and Experimental Cascade Dimensions in Cu_3Au (HEDL) 52

The average areas of simulated and observed cascades in ordered Cu_3Au irradiated with Cu^+ ions agree well when the thin foil thickness required for the observation is taken into account.

a. Microstructural Analysis of Specimens Irradiated in RTNS-II (HEDL) 60

Additional examinations of the copper-alloy series irradiated in RTNS-11 at 25°C confirm the validity of conclusions drawn in previous studies of point defect production and clustering.

9. Prediction of the Change in the Offset Yield Strength of Copper Due to High Energy Neutron Irradiation Using Vickers Microhardness Data (HEDL) 65

The relative increase in the Vickers hardness of copper irradiated to 1 x 10^{17} n/cm^2 (E ~14 MeV) is directly proportional to the increase in the 0.2% offset yield strength of copper.

CHAPTER 3. FUNDAMENTAL MECHANICAL BEHAVIOR

1. Irradiation Creep Transient in Ni-4 at. % Si (ANL) 77

Creep rate transients in Ni-4 at. % Si associated with the initiation and termination of 21 MeV deuteron irradiation at 350°C were analyzed. A short term transient observed at the end of irradiation appears to be a result of surplus vacancy flux to dislocations whereas other transients with longer durations may have resulted from a change in dislocation structure.

Page

2. Creep Fracture Mechanism in Unirradiated and Irradiated Stainless Steels (UCSB) 89

A revised creep fracture map for solution annealed 316 stainless steel was developed to include the effect of creep controlled cavity growth. Further, a new model of creep rupture for helium embrittled stainless steels was compared to data on a Ti modified 316. This "calibrated" model was used to construct a map for the embrittled stainless steels.

3. Radiation Enhanced Segregation to Grain Boundaries (PNL) 114

Radiation induced surface segregation of *phosphorus was found in both 316 type stainless steel and in Nimonic PE16 irradiated with 5 MeV Ni^{++} ions. Segregation and depletion of the other alloying elements in 316 stainless steel agreed with that reported by other investigators. No significant radiation enhanced or induced segregation was observed in the ferritic HT-9 or Ti-6Al-4V alloy.*

CHAPTER 4. CORRELATION METHODOLOGY

1. Dual-Ion Irradiations of 316 Stainless Steel (W-ARD) 121

Analytical electron microscopy of acicular precipitates in dual ion bombarded SA 316 SS shows them to be rich in Ni, Si and P. The results are in qualitative agreement with acicular precipitate compositions in austenitic stainless steels after long term aging or fission reactor irradiation. An unexpected inhomogeneity in Ti concentration in SA 316 from the MFE heat has been observed. Regions with high Ti content exhibit more than one precipitate morphology and do not experience rapid anomolous cavity growth.

Parametric studies of the dependence of critical cavity size

Page

on the magnitude and temperature dependence of surface energy and Van der Waals exclusion volume are reported. It is demonstrated that large variations in these parameters have only a minimal effect at temperatures below ~650°C.

2. The Influence of Microchemical Evolution on the Swelling of AISI 316 and Its Dependence on Stress, Temperature and Heat Treatment (ANL-W, HEDL) 141

Extraction and analysis of precipitates in irradiated AISI 316 shows that the microchemical evolution is sensitive to some variables but not others. There is an acceleration with applied stress of the radiation-induced nickel removal process at 550°C but not at 400°C. The relative swelling behavior can be correlated with the amount of nickel removal from the alloy matrix. At 400°C there appears to be a sensitivity of the level of precipitation to neutron flux and/or time in reactor.

3. The Microchemical Evolution of Irradiated Stainless Steel (HEDL) 152

The precipitates that develop during irradiation play the dominant role in the response of 300 series stainless steel alloys. This role is expressed primarily in a large change in matrix composition that may significantly alter the diffusional properties of point defects and their rate of acceptance at dislocations and voids. The major elemental participants are carbon, nickel and silicon. Much of the variability in the swelling of 316 stainless steel can be attributed to the sensitivity of the behavior of carbon and of radiation-stable precipitates to a wide range of materials and environmental parameters.

CONTENTS (Cont'd)

Page

4. Stability of the Radiation-Induced γ' Phase in 316 Stainless Steel (HEDL) 187

The γ' phase observed in AISI 316 is only stable during irradiation; hence it is expected to exhibit a sensitivity to displacement rate. It dissolves during annealing at the temperature of its formation in a manner which suggests that the dissolution rate is sensitive to the precipitate radius.

5. Extrapolation of Stress-Affected Swelling Models Into Compressive and Cyclic Stress States (HEDL) 198

Recent data confirm the existence of both microstructurally-based and microchemically-based mechanisms of stress-enhanced swelling. The Zatter mechanism is anticipated to respond to compressive or cyclic stresses in a different manner from the former mechanism, on which the current stress effect correlation is based.

6. A Kinetic Model for Helium Bombardment of Thin Foils (U.Va.) 219

A kinetic model has been developed to study the growth of bubbles in thin specimens of stainless steel irradiated by helim ions. It was found that the ratio of helium ions to vacancies in clusters decreased with increasing temperature, while vacancy clustering was enhanced by helium at all temperatures. The lack of swelling at low temperatures is not caused by thermal recombination of interstitials with vacancies but rather by the deereased defect production rate associated with a high vacancy concentration.

7. Effects of Near Surface Damage and Helium on the Performance of the First Wall (MIT) 222

Neutron irradiation of a 316 SS pressurized tube specimen with simultaneous ion bombardment and stress and temperature cycling

was completed. This sample and a similar but non-ion-bombarded sample from an earlier experiment were sectioned and analyzed by optical microscopy and SEM. The outer surface of the ion-bombarded sample is more heavily cracked than that of the neutron bombarded specimen and there is preliminary evidence of surface damage from helium recoils on the specimen inner surfaces.

8. Status of OWR and RTNS-II Irradiation Programs (HEDL) 231

HEDL-IΩ, the first DAFS irradiation in the OWR thermal reactor facility at LANL, was completed on schedule. HEDL-VR, an ongoing irradiation experiment at the RTNS-11 facility at LLNL, was reinitiated during this reporting period and is expected to attain a peak dose of 2.5×10^{18} n/cm^2, E ~14 MeV, at 90 and 290°C during the next reporting period.

9. ORR Irradiation of the MFE-II Experiment (HEDL) 233

Specimens of five alloys were irradiated in the ORR MFE-11 test and sent to HEDL for distribution to other DAFS investigators or for examination. This experiment investigated the effect of helium concentration, initial helium distribution and material starting condition on the swelling and microstructural development in the materials. The specimens have been sorted, interested investigators have been notified and a selected number of specimens have been scheduled for immersion density, electron microscopy and microhardness measurements at HEDL.