

WIPFEN

Welds p. 47
TWC 600 p. 62



Alloy Development for Irradiation Performance

Quarterly Progress Report

APRIL-JUNE 78

~~January-March 1979~~

May 1979

U.S. Department of Energy
Assistant Secretary for Energy Technology
Office of Fusion Energy

CONTENTS

FOREWORD	iii
HIGHLIGHTS	v
1. ANALYSIS AND EVALUATION STUDIES	1
1.1 RESIDUAL RADIOACTIVITY OF SEVERAL COMMERCIAL TITANIUM ALLOYS (McDonnell Douglas, University of Wisconsin, and EBASCO)	2
<p><i>The use of molybdenum, even in concentrations as low as 0.8 wt % makes the long-term radioactivity in titanium comparable to the long-term radioactivity in type 316 stainless steel and therefore complicates the reprocessing of titanium alloys. Aluminum has much the same effect as molybdenum on the long-term radioactivity; however, the level of radioactivity is 10³ times lower. Therefore aluminum-containing alloys could be reprocessed with modest shielding, but the aluminum content should be kept at 1-2 wt %. For strength and radioactivity, an attractive alloy composition could be titanium alloyed with 1-2 wt % Al, 10-14 wt % Sn, and 0.1-0.3 wt % Si.</i></p>	
2. TEST MATRICES AND TEST METHODS DEVELOPMENT	13
2.1 DESIGN OF MATERIALS IRRADIATION EXPERIMENT FOR SPECTRAL TAILORING (ORNL)	14
<p><i>In alloys containing nickel the He/dpa production ratio of a fusion reactor can be reproduced within reasonable limits by continuous or stepwise modification of the thermal-to-fast neutron flux ratio. Neutronic calculations to determine the required change in spectrum as a function of time are described.</i></p>	
2.2 HFIR IRRADIATION OF HOURGLASS FATIGUE SPECIMENS (ORNL)	20
<p><i>A capsule was designed for irradiation of hourglass fatigue specimens in HFIR. Three capsules have completed irradiation and two are undergoing irradiation. The capsule design and status of postirradiation disassembly of the first capsule are described.</i></p>	
2.3 DEVELOPMENT OF SMALL FATIGUE-CRACK GROWTH SPECIMENS FOR IN-REACTOR AND POSTIRRADIATION TESTING (HEDL)	36
<p><i>Miniature fatigue-crack growth specimens have been developed. They will allow in-reactor and postirradiation tests to be conducted efficiently, minimizing both irradiation space and temperature differential (due to gamma heating) considerations. The results to date have indicated that this specimen design produces fatigue-crack growth rate data that are in excellent agreement with results for larger, nonwelded designs and is suited for both in-reactor and postirradiation testing.</i></p>	

3.	PATH A ALLOY DEVELOPMENT — AUSTENITIC STAINLESS STEELS	41
3.1	STATUS OF HELIUM-PREINJECTED ANNEALED AND 20%-COLD-WORKED TYPE 316 STAINLESS STEEL IRRADIATED IN EBR-IT AT 500 and 625°C (ORNL)	42
	<i>Tensile specimens of annealed and 20%-cold-worked type 316 stainless steel were preinjected with 80 and 200 at. ppm He and then irradiated in EBR-11 at 500 and 625°C to fluences up to 2.3×10^{26} n/m² (>0.1 MeV). Tensile property and microstructural response is being compared with samples in which the helium is produced continuously to evaluate helium preinjection and fast reactor irradiation as a simulation technique.</i>	
3.2	INFLUENCE OF IRRADIATION ON THE PROPERTIES OF PATH A ALLOY WELDMENTS (ORNL)	47
	<i>Samples of 20%-cold-worked type 316 stainless steel containing a 16-8-2 weld were irradiated at 55°C to 4-11 dpa and 100-340 at. ppm He. For tensile tests at 300 and 700°C the ductility was reduced. At 300°C fractures occurred by transgranular shear and at 700°C by intergranular separation. All samples appear to have failed in the weld region.</i>	
3.3	STATUS OF FATIGUE TESTING FACILITY (ORNL)	54
	<i>A system for conducting fatigue tests on irradiated samples in a controlled environment (vacuum, inert gas, hydrogen, etc.) has been completed and tested outside the hot cell. The system is now being installed in the hot cell. Initial tests will be on type 316 stainless steel irradiated in HFIR.</i>	
4.	PATH B ALLOY DEVELOPMENT — HIGHER STRENGTH Fe-Ni-Cr ALLOYS	61
4.1	THE RESPONSE OF INCONEL 600 TO SIMULATED FUSION REACTOR IRRADIATION (ORNL)	62
	<i>Swelling, postirradiation tensile properties, and fracture behavior of Inconel 600 irradiated in HFIR to 4-9 dpa and 600-1800 at. ppm He are reported. The results suggest that this solid solution nickel base alloy does not offer any advantage over type 316 stainless steel.</i>	
5.	PATH C ALLOY DEVELOPMENT — REACTIVE AND REFRACTORY ALLOYS	83
5.1	MICROSTRUCTURE OF TITANIUM SCOPINC ALLOYS PRIOR TO IRRADIATION (McDonnell Douglas)	85
	<i>Studies to characterize the microstructures of the titanium scoping alloys before irradiation have begun. In general, the alpha-base alloys (Ti-6242S and Ti-5621S) are composed of a high percentage of primary alpha and transformed beta. The beta alloys, Ti-38-6-44 and Ti-15-3, are composed primarily of beta phase with alpha phase precipitates.</i>	
	<i>The alpha-beta alloy Ti-6Al-4V has a variety of microstructures, but the primary phase is alpha.</i>	

5.2	EVALUATION OF NIOBIUM ALLOY DATA BASE (McDonnell Douglas)	100
	<i>A large data base has been compiled on niobium alloys; however, the data base for any one alloy is limited. While a large amount of data exists on creep and creep rupture, most of the data are at higher temperatures and shorter times than those required for fusion devices. Data concerning the fatigue behavior at room and elevated temperature are meager, primarily because past applications were limited by creep and/or oxidation. No part of the existing data base shows that niobium-base alloys are deficient for fusion applications.</i>	
5.3	IRRADIATION INDUCED STRESS RELAXATION IN TITANIUM ALLOYS (HEDL)	106
	<i>Neutron irradiation creep rates were determined by stress relaxation measurements of four titanium alloys, Ti-6Al-4V (in three heat-treat conditions), Ti-6242S, Ti-5621S, and Ti-15-333. The superalpha alloy Ti-5621s had the greatest creep strength and the beta alloy Ti-15-333 was weakest. The calculated irradiation creep coefficients ranged from 7 to 51×10^{-30} $(\text{psi-n/cm}^2)^{-1}$ or 1 to 7×10^{-27} $(\text{MPa-n/cm}^2)^{-1}$. The data were obtained with bent beam specimens irradiated in EBR-11 (Row 7) to a fluence of 0.34×10^{22} n/cm^2 (>0.1 MeV) at about 450°C (840°F).</i>	
6.	PATH D ALLOY DEVELOPMENT — INNOVATIVE MATERIAL CONCEPTS	117
6.1	EFFECT OF ^4He and ^3H ON THE TENSILE PROPERTIES OF SAP (ORNL)	
	<i>Sintered Aluminum Product (SAP) has been doped with ^6Li and irradiated in HFIR to produce ^4He and ^3H at concentrations of 13, 270, and 1700 at. ppm and 2.0–6.7 dpa. The specimens were annealed at 300, 400, and 500°C for 1000 h after irradiation. Tensile testing (at the annealing temperatures) revealed little or no degradation in strength up to 1700 at. ppm ^4He and no loss of total elongation up to 270 at. ppm ^4He. Immersion density results show essentially no swelling at any ^4He level.</i>	
7.	STATUS OF IRRADIATION EXPERIMENTS	131
7.1	STATUS OF ORR-MFE-2 (ORNL and ANL)	132
	<i>Redesign of ORR-MFE-2 to obtain more efficient heat removal has been completed. The experiment is being assembled and reactor insertion is projected to be about July 24. The flux and spectral mapping experiment is assembled and will be irradiated shortly before insertion of ORR-MFE-2.</i>	
7.2	IRRADIATION EXPERIMENT SCHEDULE	141
8.	CORROSION TESTING AND HYDROGEN PERMEATION STUDIES	147

8.1 CAPSULE TESTS OF IRON-BASE ALLOYS IN LITHIUM (ORNL) 148

Data are reported on the compatibility between type 316 stainless steel and liquid lithium that contained either O, C, H, Al, Ti, Zr, Si, or Pb additions. The comparative corrosion resistance of a variety of 300 series stainless steels was also determined in purified lithium. Types 310 and 321 stainless steel exhibited the largest and smallest weight losses and surface degradations, respectively.

8.2 THERMAL-CONVECTION LOOP TESTS OF STAINLESS STEEL IN LITHIUM (ORNL) 158

Corrosion results are reported for two types of thermal-convection loops that circulate liquid lithium. A type 316 stainless steel loop yielded weight change results similar to those from types 304L and 321 stainless steel loops, all of which operated for 3000 h at a maximum temperature of 600°C. Weight losses of type 316 stainless steel at 600°C were measured between 500 and 5000 h, and the rate of loss decreased with time. The operating status of the loops and future test plans are discussed.

8.3 COMPATIBILITY OF BLANKET, COOLANT, AND TRITIUM-PROCESSING SALTS (ORNL) 165

Controlled amounts of HTS salt ($KNO_3-NaNO_2-NaNO_3$, 44-49-7 mol %) were reacted with lithium. A rapid, highly exothermic reaction occurred spontaneously on heating a mixture of the lithium and salt to about 180°C.

8.4 HYDROGEN PERMEATION CHARACTERISTICS OF PATH A, PATH B, AND PATH C ALLOYS (ANL) 169

Hydrogen permeability of Inconel 718 was measured at temperatures in the range 100 to 800°C at hydrogen driving pressures from 10^{-1} to 10^4 Pa. Methods of preparing permeation assemblies for titanium-base alloys are being developed.